



TAURUS 7%P-0%AG SQUARE COPPERBRAZE GAS RODS

Description

Our Taurus Copper Braze 7% Phosphorous, 0% Silver is a copper based filler metal that is self-fluxing on copper by virtue of its phosphorous content. Because of its self-fluxing nature, time and money is saved as a result of the elimination of necessary steps to flux a joint before brazing. However, copper alloys such as brass and bronze should be fluxed with our Taurus Flux to assure a sound braze joint. While this filler metal is widely used in the air conditioning and plumbing industries, it is not recommended for ferrous or nickel-based materials because the joint will become brittle and may fail. The copper phosphor alloys vary in silver content from 18% to 2% and the percentage of silver and phosphorous does change the melt and flow characteristics of the filler metal.

AVAILABLE IN

- 2.0mm – 1kg / 100g pack

SPECIFICATION

VALUE

Silver	–
Copper	93
Phosphorus	7
Melting range	710 – 820 °C
Working temperature	730 °C
	AWS A5.8M / A5.8
	EN 1044 CP 202
	DIN 8513 L-Cu
	ISO 17672 CuP 180

CLASSIFICATION

Product Category

1. Consumables
2. Gas Rods

Date Created

05 Nov 2025